

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization  
International Bureau



(43) International Publication Date  
9 August 2001 (09.08.2001)

PCT

(10) International Publication Number  
**WO 01/57945 A1**

(51) International Patent Classification<sup>7</sup>: H01M 8/12, 8/06

(21) International Application Number: PCT/NL01/00085

(22) International Filing Date: 5 February 2001 (05.02.2001)

(25) Filing Language: Dutch

(26) Publication Language: English

(30) Priority Data:  
1014284 4 February 2000 (04.02.2000) NL

(71) Applicant (for all designated States except US): **STICHT-  
ING ENERGIEONDERZOEK CENTRUM NEDER-  
LAND** [NL/NL]; Westerduinweg 3, NL-1755 LE Petten  
(NL).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **VAN BERKEL,  
Franciscus, Petrus, Felix** [NL/NL]; Geest 20, NL-1811

GH Alkmaar (NL). **OUWELTJES, Jan, Pieter** [NL/NL];  
Kabelrij 58, NL-1834 EZ Sint Pancras (NL). **NAM-  
MENSMA, Pieter** [NL/NL]; Saturnuslaan 36, NL-1702  
BC Heerhugowaard (NL).


(74) Agent: **JORRITSMA Ruurd**; Nederlandsch Octrooi-  
bureau, Scheveningseweg 82, P.O. Box 29720, NL-2502 LS  
The Hague (NL).

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU,  
AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CR, CU, CZ,  
DE, DK, DM, DZ, EE, ES, FI, GB, GD, GE, GH, GM, HR,  
HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR,  
LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ,  
NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM,  
TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW.

(84) Designated States (*regional*): ARIPO patent (GH, GM,  
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian  
patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European  
patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE,  
IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF,  
CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).

[Continued on next page]

(54) Title: METHOD OF FABRICATING AN ASSEMBLY COMPRISING AN ANODE-SUPPORTED ELECTROLYTE, AND  
CERAMIC CELL COMPRISING SUCH AN ASSEMBLY



(57) Abstract: Electrochemical cell on the basis of electrode-supported thin electrolyte comprising an anodic support (1) consisting of a nickel/zirconia material and an electrolyte layer (3) disposed comprising zirconia thereon and a cathode layer (6) which is in turn disposed thereon. To improve the quality of the cell and to increase the output it is proposed to arrange an auxiliary or intermediate layer (2) between the electrolyte layer and the anodic support. This auxiliary layer consists of nickel and zirconia particles which are substantially smaller than the particles of the support. Then an electrolyte layer (10) and, on the other side of the anodic support, a current collector layer are applied. None of these layers are sintered. Only after an assembly obtained in this manner has been obtained is a sintering treatment carried out.



WO 01/57945 A1



**Published:**

- with international search report
- before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments

*For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.*

Method of fabricating an assembly comprising an anode-supported electrolyte, and ceramic cell comprising such an assembly

The present invention relates to a method of fabricating an electrode  
5 support, comprising the steps of providing an assembly comprising an anodic support  
made of nickel/zirconia material, of applying to one side of that anodic support an  
anode auxiliary layer comprising a mixture of nickel oxide and YSZ particles on top of  
which an electrolyte layer comprising YSZ particles is applied.

Such a support is disclosed by DE-19819453 A1. There, an auxiliary layer  
10 is applied to a sintered anode support, and after a prior heat treatment an electrolyte  
layer is put onto the auxiliary layer. The assembly consisting of anode support,  
auxiliary layer and electrolyte layer is then sintered at 1400°C. A cathode is then  
applied and a further sintering treatment is carried out.

It is the object of the present invention to provide a method which  
15 incorporates the step of applying a current collector layer disposed on the other side of  
the anode support.

With a prior art method, sintering of the anode support and application of  
an auxiliary layer and/or electrolyte layer after this has been sintered is followed by the  
application of a current collector layer, after which the assembly is subjected to yet  
20 another sintering operation.

It has been found that the output of an electrochemical cell comprising such  
an assembly is not optimal, and it is the object of the present invention to improve the  
output of such a cell and its reliability. This object is achieved for an above-described  
method in that the step of providing the assembly is followed by subjecting said  
25 assembly to a sintering treatment, the anodic support and the various layers and/or  
combinations thereof of the assembly being in a nonsintered state prior to said sintering  
treatment.

It is assumed that the inventively improved characteristics of an  
electrochemical cell fabricated with the assembly according to the invention are  
30 achieved because none of the layers of which the assembly is composed has been  
subjected to a sintering treatment before the sintering treatment of the entire assembly  
is carried out. In particular, this allows the so-called sintering shrinkage to be avoided,  
i.e. the shrinkage which results in prior-art assemblies from repeated sintering of

specific layers and one-off sintering of other layers disposed thereon. Moreover, the number of sintering steps is decreased, thereby reducing production costs. According to an advantageous embodiment of the invention, the current collector layer is also applied before the assembly is sintered and is sintered together with the assembly.

5           According to the invention, the above-described sintering treatment preferably takes place at a temperature of between 1300 and 1500°C.

To impart some strength to the anodic, preferably nonsintered, support, it is possible, according to the invention, to subject this to a heat treatment at a temperature of between 900 and 1100°C, the details depending on the materials used and technical  
10 possibilities. That is to say that in principle it is possible to dispense with such a prior heat treatment of the anodic support.

Apart from the above-described layers, the assembly can moreover comprise a cathode layer and/or additional electrolyte layer or electrolyte auxiliary layer, respectively.

15           The above-described assembly allows the operating temperature of a solid oxide fuel cell to be further reduced. At present, a temperature range of 700-800°C is considered desirable. This low temperature allows the stack and system components of the cell to be constructed more cheaply. That is to say, the steel grades used can be less expensive ferritic stainless grades. Moreover, components customary for installations in  
20 the prior art can be employed, and the service life of the various components and consequently of the cell can be extended considerably.

However it has been found that at a low operating temperature the efficiency of the solid oxide fuel cell decreases. The reason for this is that the voltage losses across the cell increase with falling temperature. In the prior art it has been  
25 proposed to reduce the thickness of the electrolyte to values below 40 µm, as a result of which the voltage losses across the ceramic cell decrease and lower operating temperatures can be achieved. As thin electrolyte layers of this type have negligible mechanical strength, electrode-supported solid oxide fuel cells have been proposed. In such an arrangement, an electrolyte material in the form of a thin layer is, for example,  
30 applied to an anodic support which has been sintered. The above-described publication describes such an anode-supported thin electrolyte layer. Starting from nickel oxide and YSZ (yttrium-stabilized zirconia), a suspension is prepared which is shaped as desired

by uniaxial pressing, followed by sintering. The electrolyte layer is applied directly to the anode substrate thus prepared.

The application of an auxiliary or intermediate layer consisting of NiO/YSZ was found to result in filling of the larger pores of the anode substrate, thus producing a very flat surface of the anode support. This comparatively dense layer is comparatively thin, i.e. its effect on the diffusion of gases is comparatively small. The underlying thicker layer has greater porosity, which means that the movement of the gases is not hampered. That is to say that according to the invention a design is obtained which on the one hand has a very flat boundary without large cavities but on the other hand is sufficiently gas-permeable to permit migration of gases. According to an advantageous embodiment, the particle size chosen for the intermediate layer such that the surface of the anode support only has pores smaller than about 1  $\mu\text{m}$  and a minimum of defects or even is free from defects. This allows the electrolyte to be applied under optimal conditions to the support with the auxiliary layer. The electrolyte is thus fabricated free from defects.

According to an advantageous embodiment of the invention, the mean diameter of the pores of the auxiliary layer is below 0.5  $\mu\text{m}$ , while the underlying thicker support has pores having a mean diameter of between 0.5 and 3.0  $\mu\text{m}$ .

The porosity of the auxiliary layer in particular is about 40 vol%, while the porosity of the support is between 40 and 60 vol%.

The anodic support is fabricated, for example, by a suspension being prepared, starting e.g. from nickel oxide and zirconia material, and this being given the desired (green) shape, for example by means of sheet casting or extrusion, and possibly some strength being imparted thereto by heat treatment in the anodic support. This heat treatment can be carried out in any manner known in the prior art, at a temperature of between 900 and 1100°C over a period of from 1 to 8 hours. This treatment does not comprise any sintering. Sintering is carried out at a higher temperature.

Next, the anode auxiliary layer is applied. The technique of application to the anodic support can comprise any method known in the prior art. Since a comparatively thin layer has to be applied, the screen printing technique is particularly suitable. The layer thickness of the auxiliary layer can be between 3 and 20  $\mu\text{m}$ . Next, a layer of YSZ of the same thickness can be applied which, after the heating step, acts as the electrolyte. Next, the assembly thus obtained can undergo a sintering treatment at a

temperature of between 1300 and 1500°C. The sintering time can be about one hour. Then the cathode is embodied. Cosintering is an option. The invention moreover allows fabrication costs to be kept within limits and the production to be scaled up in a simple manner.

5           To improve the current collection on the anode side, a separate current collector is provided. This current collector can comprise nickel material. Such a current collector can be embodied by a nickel oxide layer having e.g. a layer thickness of 10-40  $\mu\text{m}$  being applied to the anode before final sintering. During operation in an electrochemical reactor, nickel oxide will be converted into nickel. Apart from acting as  
10 a current collector, the nickel layer prevents nickel depletion from the anode support during final sintering. This is because at the comparatively high sintering temperature (1300-1500°C) nickel oxide has been found to evaporate and to migrate towards the sintering plates between which sintering takes place. Placed against said current collector is a further current collector made of metallic material, such as a gauze or  
15 plate material. The sequence of the application of the various layers to the anode support can be modified as desired.

One example of the invention is illustrated in more detail with reference to the drawing. The single figure shows an anode-supported electrolyte. The anode support is indicated by 1 and consists of a nickel/zirconia layer. The thickness of this layer is  
20 between 200 and 1000  $\mu\text{m}$ . This layer serves to impart mechanical strength and should be readily gas-permeable. Moreover, because of its thickness it should lend itself to being fabricated in a comparatively inexpensive manner, for example by means of sheet casting or extrusion. Other metal-ceramic compositions are conceivable, copper and cobalt being potentially suitable as metals and titanium oxide, aluminium oxide and  
25 magnesium oxide being potentially suitable as ceramic materials. Optionally, a steam-methane reformer catalyst can be present, which converts steam and methane into carbon monoxide and hydrogen. 3 indicates the electrolyte layer, consisting of 8 YSZ. In general, the electrolyte should consist of oxygen ion-conducting ceramic materials such as ceria, zirconia and perovskites, which can be doped e.g. with lanthanide or  
30 alkaline earth metals. This layer 3 has a thickness of between 3 and 40  $\mu\text{m}$ . The anode auxiliary or intermediate layer is indicated by 2. This consists of nickel and a ceramic material such as zirconia, ceria and the like. Here again, variations are possible, and in general a combination of a metal and oxygen ion-conducting ceramic will be used,

consisting e.g. of lanthanide- or alkaline earth metal-doped ceria, zirconia or perovskites.

4 indicates a current collector layer. In the operational stage, this consists of nickel and has a thickness of between 4 and 40  $\mu\text{m}$ .

5           The current collector preferably includes a contact layer made of some metal. If nickel is used, the evaporation of nickel oxide from the support layer 1, the anode support, during sintering will be inhibited.


          Layer 5 is an additional electrolyte layer or electrolyte auxiliary layer which can be applied directly on top of electrolyte layer 3. This layer consists of lanthanide-  
10 or alkaline earth metal-doped ceria. The use of this additional electrolyte layer permits mixed-conductivity perovskite materials such as  $\text{La}_{0.6}\text{Sr}_{0.4}\text{Fe}_{0.8}\text{Co}_{0.2}\text{O}_3$  to be employed which normally react with a zirconia electrolyte but do not react with a ceria electrolyte. Layer 5 can be sintered at 1300-1500°C together with the anode support and the anode auxiliary layer and electrolyte layer disposed thereon and the current  
15 collector layer. Alternatively, this layer 5 can be sintered in a separate step after the assembly consisting of the anode support, anode auxiliary layer, electrolyte layer and current collector layer has been sintered. Layer 6 is the cathode layer, which can consist of a bilayer cathode, consisting of 1) a mixture layer of  $(\text{La},\text{Sr})\text{MnO}_3$  (LSM) and zirconia on top of this, and 2) a current-collecting layer consisting of LSM if electrolyte  
20 layer 3 only is used. In the case of electrolyte layer 5 being used as well there is the option of employing mixed-conductivity perovskite materials such as  $\text{La}_{0.6}\text{Sr}_{0.4}\text{Fe}_{0.8}\text{Co}_{0.2}\text{O}_3$  as the cathode material. Layer 6 can likewise be sintered directly with the above-described assembly and also, in a separate step, be sintered after the above-described assembly has been sintered. Those skilled in the art, having read the  
25 above, will immediately be able to think of variations which are obvious and are within the scope of the appended claims.

CLAIMS

1. Method of fabricating an electrode support, comprising the steps of providing an assembly comprising an anodic support made of nickel/zirconia material,  
5 of applying to one side of that anodic support an anode auxiliary layer comprising a mixture of nickel oxide and YSZ particles on top of which an electrolyte layer comprising YSZ particles is applied, characterized in that the step of providing the assembly is followed by subjecting said assembly to a sintering treatment, the anodic support and the various layers and/or combinations thereof of the assembly being in a  
10 nonsintered state prior to said sintering treatment.
2. Method according to Claim 1, comprising a current collector layer, which is disposed on the other side of the anodic support, includes metal particles and is in a nonsintered state prior to said sintering treatment.
3. Method according to either of the preceding claims, wherein said sintering  
15 treatment is carried out at a temperature of between 1300 and 1500°C.
4. Method according to any one of the preceding claims, wherein the step of providing an anodic support comprises a heat treatment of said anodic support at 900-1100°C.
5. Method according to any one of the preceding claims, wherein said  
20 assembly comprises a cathode layer.
6. Method according to any one of the preceding claims, wherein said assembly comprises an electrolyte auxiliary layer disposed between electrolyte layer and cathode.
7. Method according to any one of the preceding claims, wherein the step of  
25 providing the anodic support comprises the fabrication, by means of the tape casting technique or extrusion, of a plate having a thickness of between 0.3 and 1.0 mm.
8. Method according to any one of the preceding claims, wherein said auxiliary layer is applied as a suspension to the support by means of screen printing.
9. Method according to any one of the preceding claims, wherein said  
30 auxiliary layer is applied in a thickness of 3-20  $\mu\text{m}$ .
10. Method according to any one of the preceding claims, wherein a nickel oxide layer having a thickness of 10-40  $\mu\text{m}$  is applied to the inside of said support.



11. Method according to Claim 9, wherein the application step comprises screen printing.
12. Method according to any one of the preceding claims, comprising a further electrolyte layer on said electrolyte layer which comprises YSZ particles and is cosintered therewith.
13. Method according to Claim 12, wherein said further electrolyte layer comprises ceria doped with lanthanide or alkaline earth metals.
14. Method according to any one of the preceding claims, wherein the pores of said auxiliary layer have a mean diameter of less than 0.5  $\mu\text{m}$ .
15. Method according to any one of the preceding claims, wherein the pores of said anodic support have a mean diameter of 0.5-0.3  $\mu\text{m}$ .
16. Method according to any one of the preceding claims, wherein the porosity of said auxiliary layer is about 40 vol%.
17. Method according to any one of the preceding claims, wherein the porosity of said support is 40-60 vol%.
18. Method according to any one of the preceding claims, wherein the current collector layer comprises nickel.
19. Electrochemical cell comprising an assembly obtained by means of the method according to any one of the preceding claims.



# INTERNATIONAL SEARCH REPORT

Internal application No  
PCT, INT J1/00085

A. CLASSIFICATION OF SUBJECT MATTER  
IPC 7 H01M8/12 H01M8/06

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)  
IPC 7 H01M

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ, INSPEC

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
P, X	WO 00 69008 A (JOERGENSEN METTE JUHL ;BAGGER CARSTEN (DK); PRIMDAHL SOEREN (DK);) 16 November 2000 (2000-11-16) claims 1,5,6 page 10, line 11 -page 11, line 3; example II	1,3,5, 7-9,11, 19
P, Y	---	6,9, 12-14,17
	--- -/--	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

\* Special categories of cited documents:

- \*A\* document defining the general state of the art which is not considered to be of particular relevance
- \*E\* earlier document but published on or after the international filing date
- \*L\* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- \*O\* document referring to an oral disclosure, use, exhibition or other means
- \*P\* document published prior to the international filing date but later than the priority date claimed

- \*T\* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- \*X\* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- \*Y\* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- \*Z\* document member of the same patent family

Date of the actual completion of the international search

20 June 2001

Date of mailing of the international search report

04/07/2001

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax: (+31-70) 340-3016

Authorized officer

D'hondt, J

## INTERNATIONAL SEARCH REPORT

International Application No

PCT/ 01/00085

## C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
P,X	<p>DATABASE INSPEC 'Online! -  INSTITUTE OF ELECTRICAL ENGINEERS,  STEVENAGE, GB;  JORGENSEN M J ET AL: "Fabrication of thin  anode-supported SOFCs"  Database accession no. 6783862  XP002170091  abstract  &amp; FOURTH EUROPEAN SOLID OXIDE FUEL CELL  FORUM. PROCEEDINGS, FOURTH EUROPEAN SOLID  OXIDE FUEL CELL FORUM. PROCEEDINGS,  LUCERN, SWITZERLAND, 10-14 JULY 2000,  pages 203-210 vol.1,  2000, Oberrohrdorf, Switzerland, European  Fuel Cell Forum, Switzerland  ISBN: 3-905592-04-5</p>	1,5,19
Y	<p>DE 198 19 453 A (KERNFORSCHUNGSANLAGE  JUELICH) 11 November 1999 (1999-11-11)  cited in the application  column 2, line 20 - line 23; claims 1,4  column 3, line 67 -column 4, line 37  claims 1,4,5</p>	9
Y	<p>US 5 445 903 A (CABLE THOMAS L ET AL)  29 August 1995 (1995-08-29)  column 4, line 57 -column 5, line 11;  claims 1,4-6,14; figure 2; example A  column 5, line 23 - line 36  column 6, line 7 - line 11</p>	17
Y	<p>US 5 932 368 A (BATAWI EMAD ET AL)  3 August 1999 (1999-08-03)  column 3, line 1 - line 12; claims 1,4;  figure 2  column 3, line 28 - line 35</p>	14
Y	<p>US 6 007 683 A (MAKOWIECKI DANIEL M ET  AL) 28 December 1999 (1999-12-28)  claims 2,4,5; figure 3D  column 7, line 43 - line 63</p>	6,13
Y	<p>PATENT ABSTRACTS OF JAPAN  vol. 1995, no. 03,  28 April 1995 (1995-04-28)  -&amp; JP 06 349503 A (MITSUBISHI HEAVY IND  LTD), 22 December 1994 (1994-12-22)  abstract</p>	12,13
A	<p>WO 97 23007 A (FORSCHUNGSZENTRUM JÜLICH  GMBH) 26 June 1997 (1997-06-26)  page 6, line 1 - line 7; claims 1-4</p>	1

-/--

# INTERNATIONAL SEARCH REPORT

Internatic  
PCT/N

pplication No  
1/00085

## C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	DE 41 32 584 A (FUJI ELECTRIC CO LTD) 9 April 1992 (1992-04-09) column 3, line 41 -column 4, line 5; example 3 -----	1
A	WO 99 16140 A (SIEMENS WESTINGHOUSE POWER COR) 1 April 1999 (1999-04-01) page 9, line 28 -page 10, line 8; claims 1,27,35 -----	1

## INTERNATIONAL SEARCH REPORT

 Internz application No  
 PCT, ... 1/00085

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 0069008 A	16-11-2000	AU 4391900 A	21-11-2000
DE 19819453 A	11-11-1999	NONE	
US 5445903 A	29-08-1995	AU 686227 B AU 7643394 A CA 2171114 A CN 1133648 A,B EP 0721675 A JP 9505684 T NZ 273209 A WO 9507554 A US 5589285 A	05-02-1998 27-03-1995 16-03-1995 16-10-1996 17-07-1996 03-06-1997 25-09-1996 16-03-1995 31-12-1996
US 5932368 A	03-08-1999	EP 0788175 A AT 191815 T AU 707763 B AU 1239397 A DE 59604956 D DK 788175 T JP 9223508 A	06-08-1997 15-04-2000 22-07-1999 07-08-1997 18-05-2000 10-07-2000 26-08-1997
US 6007683 A	28-12-1999	US 5753385 A	19-05-1998
JP 06349503 A	22-12-1994	NONE	
WO 9723007 A	26-06-1997	DE 19547700 A AU 713760 B AU 1869697 A DE 59603513 D DK 868761 T EP 0868761 A JP 2000501879 T US 6048636 A	10-07-1997 09-12-1999 14-07-1997 02-12-1999 03-04-2000 07-10-1998 15-02-2000 11-04-2000
DE 4132584 A	09-04-1992	JP 5003037 A US 5122425 A	08-01-1993 16-06-1992
WO 9916140 A	01-04-1999	US 5908713 A EP 1032953 A TW 382830 B	01-06-1999 06-09-2000 21-02-2000